📥 American National Rubber

PO Box 878 \*\* Ceredo, West Virginia 25507 \*\* Telephone: 1-800-624-3410 \*\* Fax: 304-453-2347

## DATA SHEET

Deleted:	¶
----------	---

NEOPRENE/EPDM/S	BR BLEND	4511-N	
Color:		Black	
Specifications:	ASTM D-1056-00 ASTM D-1056-67(1) SAE J18-02 GM 6086M(3) GMN11106(3)	2A5 SCE 45 2A5 IIIB <u>IIIB</u>	<b>Formatted:</b> Font: 8 pt
25% Compression Defl	ection (PSI)	17 - 24	
Shore 00 Durometer (A	Approximate)	65+	
Density (Approximate p	p.c.f.)	12 - 20	
Water Absorption By W	/eight	5%	
Temperature Range		-70 to 225 F	
Weather Resistance:	UV Ozone	Fair Good	
Accelerated Linear Shri	nkage (Typical)	5%	
Tensile Strength (Typic	cal)	90 PSI	
Elongation (Typical)		100%	
Flammability:	FM VSS No. 302	Pass	
(1)Obsolete specification	listed for reference only ANR certifies	to most recent revision of ASTM	

(1)Obsolete specification listed for reference only. ANR certifies to most recent revision of ASTM D-1056 and SAE J18.

(3)Certain sections of this specification will not apply to all products. Contact Customer Service for details.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.

ISO 9001-2000 Certified Company

<u>06/06</u>	Deleted: 01/03